

DRILLING (SOLID CARBIDE)

MWE

CARBIDE

RECOMMENDED CUTTING CONDITIONS

Work Material	Mild Steel ($\leq 180\text{HB}$)			Carbon Steel, Alloy Steel (180—280HB)			Carbon Steel, Alloy Steel (280—350HB)		
	Ck10			Ck45, 42CrMo4			36CrNiMo4		
Drill Dia. (mm)	Revolution (min^{-1})	Feed rate (Min.—Max.) (mm/rev)		Revolution (min^{-1})	Feed rate (Min.—Max.) (mm/rev)		Revolution (min^{-1})	Feed rate (Min.—Max.) (mm/rev)	
3.0	6400	0.1	(0.06—0.13)	5900	0.1	(0.06—0.13)	5400	0.09	(0.06—0.12)
4.0	5500	0.12	(0.08—0.16)	5100	0.12	(0.08—0.16)	4700	0.11	(0.07—0.14)
5.0	4400	0.15	(0.10—0.20)	4100	0.15	(0.10—0.20)	3800	0.14	(0.09—0.18)
6.3	4000	0.2	(0.13—0.26)	3700	0.2	(0.13—0.26)	3500	0.18	(0.11—0.24)
8.0	3300	0.23	(0.18—0.28)	3100	0.23	(0.18—0.28)	2900	0.21	(0.16—0.25)
10.0	2800	0.27	(0.22—0.32)	2700	0.27	(0.22—0.32)	2500	0.23	(0.19—0.27)
12.0	2500	0.31	(0.28—0.34)	2300	0.31	(0.28—0.34)	2200	0.26	(0.23—0.29)
16.0	1900	0.33	(0.28—0.38)	1700	0.33	(0.28—0.38)	1600	0.29	(0.24—0.33)
20.0	1500	0.35	(0.30—0.40)	1400	0.35	(0.30—0.40)	1300	0.3	(0.26—0.34)

Work Material	Austenitic Stainless Steel ($\leq 200\text{HB}$)			Gray Cast Iron ($\leq 350\text{MPa}$)			Ductile Cast Iron ($\leq 450\text{MPa}$)		
	X5CrNi1810, X5CrNiMo17-12-2			GG30			GGG45		
Drill Dia. (mm)	Revolution (min^{-1})	Feed rate (Min.—Max.) (mm/rev)		Revolution (min^{-1})	Feed rate (Min.—Max.) (mm/rev)		Revolution (min^{-1})	Feed rate (Min.—Max.) (mm/rev)	
3.0	1900	0.07	(0.05—0.08)	6900	0.1	(0.06—0.13)	6400	0.1	(0.06—0.13)
4.0	1500	0.08	(0.06—0.10)	5500	0.12	(0.08—0.16)	5100	0.12	(0.08—0.16)
5.0	1200	0.1	(0.07—0.13)	4400	0.15	(0.10—0.20)	4100	0.15	(0.10—0.20)
6.3	1200	0.13	(0.09—0.17)	3700	0.2	(0.13—0.26)	3500	0.2	(0.13—0.26)
8.0	900	0.14	(0.10—0.18)	2900	0.25	(0.18—0.31)	2700	0.23	(0.18—0.28)
10.0	700	0.16	(0.12—0.19)	2300	0.29	(0.22—0.35)	2200	0.27	(0.22—0.32)
12.0	600	0.18	(0.15—0.20)	2100	0.33	(0.28—0.37)	1900	0.31	(0.28—0.34)
16.0	400	0.19	(0.15—0.23)	1500	0.35	(0.28—0.42)	1400	0.33	(0.28—0.38)
20.0	300	0.2	(0.15—0.24)	1300	0.37	(0.30—0.44)	1200	0.35	(0.30—0.40)

Work Material	Aluminium Alloy ($\text{Si} < 5\%$)			Heat Resistant Alloy			Hardened Steel (40—55HRC)		
				Inconel718			X40CrMoV51, 55NiCrMoV7		
Drill Dia. (mm)	Revolution (min^{-1})	Feed rate (Min.—Max.) (mm/rev)		Revolution (min^{-1})	Feed rate (Min.—Max.) (mm/rev)		Revolution (min^{-1})	Feed rate (Min.—Max.) (mm/rev)	
3.0	7900	0.1	(0.06—0.13)	1900	0.07	(0.05—0.09)	1900	0.07	(0.05—0.09)
4.0	6300	0.12	(0.08—0.16)	1500	0.09	(0.06—0.11)	1500	0.09	(0.06—0.11)
5.0	5000	0.15	(0.10—0.20)	1200	0.11	(0.08—0.14)	1200	0.11	(0.08—0.14)
6.3	4500	0.2	(0.13—0.26)	1200	0.14	(0.09—0.19)	1200	0.14	(0.09—0.19)
8.0	3500	0.23	(0.18—0.28)	900	0.14	(0.11—0.17)	900	0.14	(0.11—0.17)
10.0	2800	0.27	(0.22—0.32)	700	0.16	(0.12—0.19)	700	0.16	(0.12—0.19)
12.0	2600	0.31	(0.28—0.34)	600	0.16	(0.13—0.18)	600	0.16	(0.13—0.18)
16.0	1900	0.33	(0.28—0.38)	400	0.18	(0.14—0.21)	400	0.18	(0.14—0.21)
20.0	1700	0.35	(0.30—0.40)	400	0.19	(0.15—0.22)	400	0.19	(0.15—0.22)

DRILLING